

ABSTRACT

An anisotropic conductive adhesive sheet comprising at least a curing agent, a curable insulating resin and conductive particles, wherein in a region extending from a one-side surface of the anisotropic conductive adhesive sheet along the thickness direction to a position of not greater than 2.0 times the average diameter of the conductive particles, 90% or more of the sum of conductive particles are present, the 90% or more of the sum of conductive particles being present without contact with other conductive particles, and wherein the average diameter of conductive particles is in the range of 1 to 8 μm , the average particle distance between adjacent conductive particles being in the range of 1 to 5 times the average particle diameter and not greater than 20 μm , and wherein the thickness of the anisotropic conductive adhesive sheet is at least 1.5 times the average particle distance but not greater than 40 μm .